

**UFO Rainwater outlets**  
5mm thick unreinforced SBS modified bituminous membrane

Characteristic	Procedure	Units	Expression of result	Value or statement
<b>Thickness</b>	EN 1849-1	mm	MDV	5,0 ± 0,3
<b>Filler content</b>				0%
<b>Mass</b>	EN 1849-1	kg/m <sup>2</sup>	MDV	5,4 ± 0,54
<b>Water tightness to liquid water</b>	EN 1928	KPa	MLV	300
<b>Tensile properties:</b>				
<b>Elongation at break</b>	NEN ISO 37	%	MLV	1500
<b>Durability of water vapour resistance against artificial ageing</b>	EN 1296 and EN 1931	-	Pass	Pass
<b>Flow Resistance at elevated temperature</b>	BAM 7.06	°C	MLV	90
<b>Softening point (ring and ball)</b>	EN 1427	°C	MLV	125°C
<b>Impact Resistance: Aluminium EPS 150</b>	EN 12691	mm mm	MLV MLV	500 2000
<b>Low temperature flexibility</b>	EN 1109	°C	MLV	-20
<b>Reaction to fire</b>	EN 13501-1	-	Euroclass	F
<b>Visible Defects</b>	EN 1850-1	-	Visible defects	no visible defects
<b>MLV = Manufacturers Limiting Value</b>				
<b>MDV = Manufacturers Declared Value</b>				